

9th International Workshop on Electrodeposited Nanostructures

Soft gold coatings: influence of additives and pulse plating

Luca Magagnin, Pietro Luigi Cavallotti

Dip. Chimica, Materiali e Ing. Chimica G. Natta – Politecnico di Milano
Via Mancinelli, 7 – 20131 Milano, Italy
luca.magagnin@polimi.it

Soft gold for electronics or other applications can be obtained by controlling the structure by metal additions into the electrolyte and also by electrodeposition with very short current pulses and long off times. Soft gold is obtained from baths containing a small quantity of thallium ions as an additive, while hard gold is obtained from similar baths with nickel ions as an alternative additive. By referring to the normality inertia electrokinetic behaviour of the elements in aqueous solutions, it is shown that normal metal ions addition give soft gold deposits, while inert metal addition give hard gold layers. The main influence of normal metal addition is a decrease in the cathodic voltage during deposition, with decrease in inhibition condition coming from complexant interaction with the cathodic surface. A similar effect can be obtained with pulsed current, when the voltage increase is limited, favouring the capacitance charging with respect to the faradaic discharge. In these conditions, lateral growth prevails with respect to outgrowth, which becomes predominant in inhibition conditions. Cyanide and sulphite gold baths show a similar behaviour with respect to inhibition phenomena by complexant at surfaces.