

9th International Workshop on Electrodeposited Nanostructures

Optimizations of Pulsed Plated p and n-type Bi₂Te₃-Based Ternary Compounds by Annealing in Different Ambient Atmospheres

Christian Schumacher¹, Klaus G. Reinsberg², Raimar Rostek³, Lewis Akinsinde¹, Svenja baessler¹, Sebastian Zastrow¹, Geert Rampelberg⁴, Peter Woias³, Christophe Detavernier⁴, José A. C. Broekaert², Julien Bachmann¹, Kornelius Nielsch¹

e-Mail: lewis.akinsinde@physik.uni-hamburg.de

- [1] University of Hamburg - Institute of Applied Physics Jungiusstrasse 11, 20355 Hamburg, Germany
- [2] University of Hamburg - Institute of Applied and Inorganic Chemistry Martin-Luther-King-Platz 6, 20146 Hamburg, Germany
- [3] University of Freiburg Department of Microsystems Engineering (IMTEK) Georges-Koehler-Allee 102, 79110 Freiburg, Germany
- [4] University of Ghent - Department of Solid State Sciences Krijgslaan 281/S1, 9000 Ghent, Belgium

This work presents a comprehensive study of the fabrication and optimization of electrodeposited p – and n – type thermoelectric films. The films are deposited on Au and stainless steel substrates over a wide range of deposition potentials. The influence of the preparative parameters such as the composition of the electrolyte bath and the deposition potential are investigated. In addition, a tailor – made n – type thermoelectric ternary compound (Bi_{1-x}Sb_x)₂Te₃ by combining both the p – type SbTe and n – type BiTe electrolyte baths is examined as well. Then, the p-doped (Bi_xSb_{1-x})₂Te₃ and the n – doped Bi₂(Te_xSe_{1-x})₃ films are annealed for a period of about 1 h under helium and under tellurium atmosphere at 250 °C for 60h. Annealing in He already leads to significant improvements in the thermoelectric performance. Furthermore, due to the equilibrium conditions during the process, annealing in Te atmosphere leads to a strongly improved film composition, charge carrier density and mobility. The Seebeck coefficients increase to values up to +182 μV K⁻¹ for p – doped and –130 μV K⁻¹ for n – doped materials at room temperature. The power factors also exhibit improvements with 1320 μW m⁻¹ K⁻² and 820 μW m⁻¹ K⁻² for p – doped and n – doped films, respectively. Additionally, in-situ XRD measurements performed during annealing of the films up to 600K under He atmosphere show stepwise improvements of the crystal structure leading to the improvements in thermoelectric parameters. A thermal conductivity between 1.2 W m⁻¹ K⁻¹ and 1.0 W m⁻¹ K⁻¹ has been determined.